

10/609,179

Amendments to the Claims

1. (previously presented): A method for making an impregnated textile synthetic leather, the method comprising:

(a) impregnating a non-woven or woven textile with a polyurethane dispersion comprised of a nonionizable polyurethane and an external stabilizing surfactant; and

(b) exposing the impregnated textile to water containing a coagulant for a coagulation time sufficient to coagulate the dispersion

wherein the coagulant is a multivalent cation neutral salt.

2. (original): The method of Claim 1, wherein the method is carried out in an environment containing less than about 2000 parts per million by weight of an organic solvent.

3. (original): The method of Claim 1, wherein the method is carried out essentially free of an organic solvent.

4. (cancelled)

5. (previously presented): The method of Claim 1, wherein the coagulant is an alkaline earth cation salt.

6. (original): The method of Claim 5, wherein the coagulant is calcium nitrate, magnesium nitrate, strontium nitrate and barium nitrate or mixture thereof.

7. (original): The method of Claim 3, wherein the polyurethane dispersion contains non-polyurethane polymeric particles.

8. (previously presented): The method of Claim 1, wherein the coagulation time is at most 2 minutes.

9. (previously presented): The method of Claim 8, wherein the coagulation time is at most 1 minute.

62674A

-3-

10/609,179

10. (previously presented): The method of Claim 9, wherein the coagulation time is at most 30 seconds.

11. (original): The method of Claim 1, further comprising leaching the impregnated textile after step (b) by exposing the impregnated textile to water.

12. (original): The method of Claim 1, wherein the polyurethane dispersion contains a thickener.

13. (original): The method of Claim 12 wherein the thickener is water soluble thickener that is not ionizable.

14. (original): The method of Claim 13 wherein the thickener is a methylcellulose ether.

15. (original): The method of Claim 1 further comprising applying a frothed polymeric dispersion after step (b) to form a synthetic leather having a poromeric layer thereon.

16. (original): The method of Claim 15 wherein the frothed polymeric dispersion is an aqueous externally stabilized polyurethane dispersion.

17. (original): The method of Claim 16 wherein the poromeric layer is heated sufficiently to dry and cure the poromeric layer and then is leached in water.

18-27 (canceled).

28. (withdrawn): A synthetic leather comprised of a textile having a plurality of fibers wherein the textile has therein a polyurethane and a multivalent cation substantially water insoluble salt of an organic acid.

29. (withdrawn): The synthetic leather of Claim 28 wherein the organic acid is butyric acid; hexanoic acid; octanoic acid; decanoic acid; dodecanoic acid; lauric acid; myristic acid; palmitic acid; oleic acid; linoleic acid; stearic acid; linolenic acid; dodecylbenzene sulfonic acid; or mixture thereof.

10/609,179

30. (withdrawn): The synthetic leather of Claim 28 wherein the multivalent cation of the water insoluble salt is an alkaline earth.

31. (withdrawn): The synthetic leather of Claim 30 wherein the multivalent cation is calcium.

32. (withdrawn): The synthetic leather of Claim 28, wherein the textile has a permeable polymeric poromeric layer thereon.

33. (withdrawn): The synthetic leather of Claim 32, wherein the poromeric layer is polyurethane.

34. (withdrawn): The synthetic leather of Claim 33 wherein the polyurethane of the poromeric layer is of an aqueous externally stabilized polyurethane essentially free of any organic solvent.

35. (withdrawn): The synthetic leather of Claim 32, wherein the porous cellular coating has uniformly spherical pores having an average size between about 300 micrometers squared to 25000 micrometers squared by number.

36. (withdrawn): A synthetic leather comprised of a textile having a poromeric layer comprised of polyurethane thereon wherein the synthetic leather has an amount of a surfactant of at least a trace amount to at most about 4% by weight of the poromeric layer and a wet ply adhesion of at least about 1.5 kg/cm.

37. (withdrawn): The synthetic layer of Claim 36, wherein the amount of surfactant is at most about 2% by weight of the poromeric layer.

38. (withdrawn): The synthetic leather of Claim 36, wherein the poromeric layer has uniformly spherical pores having an average size between about 300 micrometers squared to 25000 micrometers squared by number.

39. (withdrawn): The synthetic leather of Claim 36, wherein the synthetic leather has a wet ply adhesion of at least about 2.0 kg/cm.

10/609,179

40. (withdrawn): The synthetic leather of Claim 38 wherein the poromeric layer polyurethane is of an externally stabilized polyurethane dispersion.

41. (withdrawn): The synthetic leather of Claim 36 wherein the synthetic leather was prepared in an environment essentially free of an organic solvent.

42. (withdrawn): The synthetic leather of Claim 36 wherein the textile was impregnated with a polymer.

43. (withdrawn): The synthetic leather of Claim 42 wherein the polymer was polyurethane.